

Serving Canada since 2003

## **COMPARISON CHART**

	FRP Structural Shapes	FRP Rod and Bar	Steel	Stainless Steel	; Aluminum	PVC	Douglas Fir	s Redwood
Specific Gravity	1.6 - 1.75	1.9 - 2.0	7.85	7.97	2.5	1.38	0.51	0.42
Density (Ibs/in³.)	07075	062070	0.284	0.29	0.098	0.05	0.019	0.015
Coefficient of Linear Thermal Expansion 10 <sup>6</sup> in <i>l</i> in/F	8	6	6.5	.10	.13	40	2	.3
Ultimate Strength (psi)	30,000	90,000	60,000	80,000.	30,000	6,800	12,000	8,900
Modulus of Elasticity (psi).	2.8 x 16	4.0 x 10 <sup>6</sup>	30 x 10 <sup>6</sup> .	29 x 10 <sup>6</sup>	10 x 10 <sup>6</sup>	38 x 10 <sup>6</sup>	1.5 x 10 <sup>6</sup>	51.2 x 10 <sup>6</sup>

Engineered Structures Canada Suite #1552 5328 Calgary Trail Edmonton, Alberta, Canada T6H 4JB Phone: (780) 455-9682 Fax: (780) 439-7289 email: engineeredstructures@shaw.ca